

date  
08/03/2019

## **TEST REPORT 19-0191-01**

### **Samples received :**

<b><u>Name</u></b>	<b><u>Date of receipt</u></b>
<b>Superflex</b> Pile material: 100% PES Surface structure: Needlefelt Total mass (g/m <sup>2</sup> ): 280 g/m <sup>2</sup> Total thickness (mm): 4.4 mm	21/02/2019

**Aim of the test :** Determination of the fire behaviour

### **Test conditions :**

#### **Small flame test**

Standard: **ISO 11925-2 (2010 + AC 2011)\***

Method: The use surface of a vertically put specimen placed (loose laid) on a fibre cement board (according to EN 13238) is ignited by a propane gas flame. Under condition of a surface flame attack with 15 s exposure time, there shall be no flame spread in excess of 150 mm vertically from the point of the test flame within 20 s from the time application.

If the boundary line is not reached within 20 s, the sample meets the requirements for the class E<sub>fl</sub>.

Number of tests: 3 lengthwise and 3 crosswise

Conditioning: 23 ± 2 °C and 50 ± 5 % R.H.

samples:

**Fire Behaviour**

Standard: **EN ISO 9239-1 (2010)\***  
Method: Before the test the samples are **not cleaned**.  
A floorcovering is put on **(loose laid)** to a fibre cement board (according to EN 13238). During the test, the specimen is irradiated by a gas radiator at an angle of 30°. A small flame is used to ignite the specimen. The specimen is ignited during 10 minutes. In case of inflammable specimens, the test lasts until the flame is extinguished, but 30 minutes at the most. The criterion is the burned length, from which the critical radiant flux is deduced using a calibration curve.

Number of tests: 4  
Conditioning samples: 23 ± 2 °C and 50 ± 5 % R.H.

The tests were finished in week 11/2019

## **OBTAINED RESULTS**

### **Small flame test**

Ignition time : 15 s

#### **Lengthwise**

Sample	Burning time (s)	After glowing time (s)	Boundary line reached within 20 s
1	> 60 sec	-	no
2	> 60 sec	-	no
3	56 sec	-	no

#### **Crosswise**

Sample	Burning time (s)	After glowing time (s)	Boundary line reached within 20 s
1	45 sec	-	no
2	47 sec	-	no
3	38 sec	-	no

### **Fire behaviour**

Specimen number	1 Length	2 Width	3 Length	4 Length	Average Specimens 1,3,4
Flame spread after 10 min (mm)	0	0	0	0	
Flame spread after 20 min (mm)	0	0	0	0	
Flame spread after 30 min (mm)	0	0	0	0	
Flame spread at extinction (mm)	0	0	0	0	
Flame time	12min 0s	12min 0s	12min 0s	12min 0s	
Critical heat flux CHF at extinction (kW/m <sup>2</sup> )	11.1	11.1	11.1	11.1	>11
Total smoke production at end of test (%.min)	5	1	1	8	4

**LIEDTS Eddy**  
Technician

Didier Van Daele  
Head of Floor covering and Fire Tests

Prof. Dr. Paul KIEKENS, dr. h. c.  
Director

## **ENCLOSURE TO REPORT 19-0191-01**

***Classification according to EN 13501 –1 (2007 + A1: 2009)\****

<b>Classification</b>	<b>EN ISO 11925-2 (ignition time = 15 s)</b>	<b>EN ISO 9239-1 (test period = 30 min)</b>	<b>CLASS</b>
B <sub>fl</sub>	F <sub>s</sub> ≤ 150 mm in 20 s	Critical flux ≥ 8.0 kW/m <sup>2</sup>	<b>X</b>
C <sub>fl</sub>	F <sub>s</sub> ≤ 150 mm in 20 s	Critical flux ≥ 4.5 kW/m <sup>2</sup>	
D <sub>fl</sub>	F <sub>s</sub> ≤ 150 mm in 20 s	Critical flux ≥ 3.0 kW/m <sup>2</sup>	
E <sub>fl</sub>	F <sub>s</sub> ≤ 150 mm in 20 s	No demand	
F <sub>fl</sub>	No demand	No demand	

***Additional classification smoke development according to EN 13501-1 (2007 + A1:2009)\****

		<b>CLASS</b>
Smoke development ≤ 750%.min	s1	<b>X</b>
Smoke development > 750%.min	s2	